

Product Specification Sheet

#67 Gravel

Crushed, washed and graded river rock aggregate meeting ASTM C33 size #67.


Typical Applications

Ready Mix Concret

Gradation Test — ASTM C33

Sieve Size	% Passing	Required % Passing
1 in	100	100
3/4 in	93	90-100
3/8 in	42	25-55
No. 4	6	0-10
No. 8	2	0-5
No. 200	0	0-1

Properties	Test Value	Required Spec.
Abrasion	23	50% Max
Specific Gravity	2.55	2.55 - 2.70
Absorption	0.40	0.5% - 2.0%
Soundness	9	18% max
Materials Finer than No 200 Sieve in Mineral Aggregates by Washing	0.80	1.5 max



July, 2026