

Product Specification Sheet

Cyclone Sand

Natural fine aggregate, washed and processed to meet TxDOT aggregate for surface treatments.

Typical Applications

Hot Mix Asphalt Concrete

Gradation Test — TxDOT Item 341 – Table 2

Sieve Size	Cumm. % Retained	Required Cumm. % Retained
3/8 in	100	100
No. 8	99	70-100
No. 200	6	0-30

Aggregate Quality Requirements	Test Value	Required Spec.
Linear Shrinkage, %	1.9	3 Max
Sand Equivalent, %	45	45 Min