

Product Specification Sheet

Grade 4 Gravel

Crushed and graded river rock aggregate meeting TxDOT aggregate for surface treatments.

Typical Applications

Hot Mix Asphalt Concrete

Gradation Test — TxDOT Item 302 – Table 2

Sieve Size	Cumm. % Retained	Required Cumm. % Retained
5/8 in	0	0
1/2 in	1	0-5
3/8 in	20	20-45
No. 4	95	95-100
No. 8	100	98-100

Aggregate Quality Requirements	Test Value	Required Spec.
Decantation, %	0.80	1.5 Min
Los Angeles Abrasion, %	23	35 Max
Soundness	0.40	25 Max
2 Crushed Faces, %	96	85 Min
Flakiness Index, %	0	17 Max