

Product Specification Sheet

Grade 5 Screenings

Crushed and graded river rock aggregate meeting TxDOT aggregate for surface treatments.

Typical Applications

Hot Mix Asphalt Concrete

Gradation Test — TxDOT Item 341 – Table 2

Sieve Size	Cumm. % Retained	Required Cumm. % Retained
3/8 in	100	100
No. 8	77	70-100
No. 200	14	0-30

Aggregate Quality Requirements	Test Value	Required Spec.
Linear Shrinkage, %	1.7	3 Max
Sand Equivalent, %	46	45 Min