

Product Specification Sheet

Masonry Sand

Natural fine aggregate, washed and processed to meet ASTM C144.

Typical Applications

Masonry Mortar Concrete

Gradation Test — ASTM C144

Sieve Size	Cumm. % Retained	Required Cumm. % Retained
No. 4	100	100
No. 8	100	95-100
No. 16	98	70-100
No. 30	70	40-75
No. 50	33	10-35
No. 100	7	2-15
No. 200	2	0-5

